



brentwood plastics, inc.

**3122 Sutton Boulevard
Maplewood, MO 63143**

www.brentwoodplastics.com

**Phone: 314.968.1135
Fax: 314.968.4276**

PCO29

PCO29 is a high clarity film designed for retail bag packaging. Offers unique combination of low seal initiation temperature and stiffness for maximum cycle speed on automatic wicketers. Strong seals make it a natural for whole produce bags.

Typical Properties *

<u>Property</u>	<u>Test Method</u>	<u>Typical Value</u>	<u>Unit</u>
Haze	ASTM D 1003	6	%
Gloss 45°	ASTM D 2457	74	-
Secant Modulus	ASTM D 882	42,000 MD 41,500 TD	psi
Dart Impact F 50	ASTM 1709 A	210	gm
Tensile Elongation	ASTM D 882		%
MD Yield		19	
Break		355	
TD Yield		16	
Break		720	
Coefficient of Friction untreated to untreated	ASTM D 1894	0.18	

* good faith estimates based on nominal 1.5 mil film @ 2.05 BUR
Not to be construed as specification limits
It is the users responsibility to determine suitability for any application, no warranties are expressed or implied.